SANQI STEEL FIBER

GLUED HOOK STEEL FIBER

Glued hooked steel fiber: Glueding single hooked steel fiber one by one in line with water soluble glue to keep the steel fibers evenly dispersed, no gobbet

Dispersion for first time: putting the steel fibers to conveyor, the glued steel fiber as a whole dispersed to every corner.

Dispersion for second time: after first dispersion, water soluble glue begins to dissolve, the whole glued steel fiber in each corner begins to disperse and become many single steel fiber, then, become a three-dimensional netting, increasing reinforcement effect.

Material: round cold drawn steel wire.

Wire diameter(D):0.75mm (±0.02mm)

Fiber length(L):35mm (\pm 0.05mm)

Aspect ratio L/D: 47 Tensile strength:>1100Mpa Elongation at break:<4% Appearance: bright and clean wire



Package and storage

20kg/damp-proof poly and paper composite bag.50bags bags/pallet, or 1 ton/big bag, then pallet.The pallets should be protected against rain and snow

Product Standard

EN14889-1type1(cold drawn wire) SATM A820/A820M-04 type1(cold drawn wire) YB/T5294-2009

Features & benefits (comparing with common concrete)

Tensile strength	Against pressure	Against shear (%)	Against bending (%)	Against impact (%)	Against fatigue (%)	Wear resistance
(%)	(%)					(%)
50-70 ↑	8-10 ↑	50-100 ↑	120-180 ↑	200-700 ↑	50-60 ↑	25-35 ↑

min dosage 15kg/M3

Application

Industrial floor, Tunnel, Mining, Bridge, Highway pavement, Airport.

Anping Sanqi Steel fiber & gabion co., Itd

Website: www.sqgabion.com